


WHITE METALIZED PET

WHITE METALIZED PET - is white film that is metalized on the chemical coated side with the other side corona treated polyester film. This film is suitable for flexible packaging applications and has excellent gloss & barrier properties.



SR. NO	PROPERTIES		TEST METHOD	UNIT		TARGET	мінімим	MAXIMUM	
GENERAL									
1	Thickness		Internal	Micron		12.00	11.64	12.36	
ı	HIICKHESS			Guage		48.00	46.56	49.44	
2	Yield		Internal	sq in/lb		40.687	39.498	41.945	
MECHANICAL									
1	Tensile Strength at break		ASTM D 882	Kg/cm²	MD/TD	2100	1900	2300	
'				(Kpsi)		29.9	27.0	32.7	
2	Elongation at break		ASTM D 882	%	MD	130	90	170	
2					TD	120	80	160	
3	Co-efficient of friction One side to Other side		ASTM D 1894	-	Static	0.60	0.50	0.70	
					Dynamic	0.55	0.45	0.65	
4	Metal Bond Strength		TP-105-92	gm/25 mm		800	700	900	
THERMAL									
1	Shrinkage @ 150°C/30'		ASTM D 1204	%	MD	2.0	1.6	2.6	
					TD	0.4	0.0	0.8	
2	Melting Point		Internal	°C		252	250	255	
SURFACE TREATMENT LEVEL									
1	Corona Treated Level		ASTM D 2578	Dynes/cm		52	50	54	
BARRIER									
	Optical Density			M.V.T.R. (ASTM F 1249)			O.T.R. (ASTM D 3985)		
	(JBF Method)			gm/m²/day (38°C 90% RH)			cc/m²/day (23°C 0% RH)		
Target	Minimum	Maximum	Target	Minimum	Maximum	Target	Minimum	Maximum	
2.2	2.0	2.4	0.9	0.7	1.1	1.0	0.8	1.2	
2.5	2.3	2.7	0.7	0.5	0.9	0.8	0.6	1.0	
2.8	2.6	3.0	0.5	0.3	0.7	0.6	0.4	0.8	
3.0	2.8	3.2	0.3	0.2	0.5	0.4	0.2	0.6	

^{*} MD = Machine Direction, * TD = Transverse Direction

Storage & Handling: Needs to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing.

Food Contact: Complies with EC (EU 202/2014 & EU 10/2011) and FDA (21 CFR § 175.105 & 21 CFR § 175.300) regulations on packaging for direct contact with foodstuffs. Specific document and MSDS are available on request.

Disclaimer: The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. StockPKG makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract.