

DESCRIPTION


StockPKG 200ga PET // PP-mLLDPE Lidding Film - Non-Barrier lamination offers a moderate moisture barrier, lock seal for PP containers, and a robust sealant layer for closures.

FEATURES

- Moderate Moisture Barrier
- Available in Clear
- White also Available as a Special Order
- Lock Seal to PP Containers
- Strong seal to HDPE Containers

APPLICATIONS

- Lidding for many types of Food Packaging Applications that do not require a high barrier.



48ga PET

1.5 Mil PP-mLLDPE

PROPERTIES		TEST METHOD	UNIT	TYPICAL VALUE
PHYSICAL PROPERTIES				
Thickness		Internal	Gauge	200
Yield			in ² /lb	13,187
MECHANICAL PROPERTIES				
Tensile Strength	MD	ASTM D 882	psi	8,400
	TD			7,500
Elongation Break	MD	ASTM D 882	%	90
	TD			80
SURFACE PROPERTIES				
COF PET		ASTM D 1894	St	0.45
			Dy	0.45
PE COF				0.2
Surface Tension		ASTM D 2578	Dyne / cm	48
OPTICAL PROPERTIES				
Haze		ASTM D 1003	%	14
Gloss - 45 ⁰		ASTM D 2457	GU	75
THERMAL PROPERTIES				
Seal Initiation Temp			Fahrenheit	270
BARRIER PROPERTIES				
WVTR, 38°C, 90% RH		ASTM F 1249	gm / 100in ² / day	0.42
OTR 23°C, 0% RH		ASTM D 1434	cc / 100in ² / day	7.9

MD = Machine Direction

TD = Transverse Direction

Storage & Handling: Needs to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing. **Food Contact:** Complies with EC (EU 202/2014 & EU 10/2011) and FDA (21 CFR § 175.105 & 21 CFR § 175.300) regulations on packaging for direct contact with foodstuffs. Specific document and MSDS are available on request.

Disclaimer: The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. StockPKG makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract.